PATENT ABSTRACTS OF JAPAN

(11)Publication number:

07-022227

(43) Date of publication of application: 24.01.1995

(51)Int.CI.

H01F 1/08

C22C 33/02

C22C 38/00

(21)Application number : 05-300773

(71)Applicant: TOSHIBA CORP

(22)Date of filing:

08.11.1993

(72)Inventor: TSUDAI AKIHIKO

SAKAI ISAO

MIZOGUCHI TETSUHIKO

INOMATA KOICHIRO

(54) PRODUCTION OF PERMANENT MAGNET

(57) Abstract:

PURPOSE: To produce a permanent magnet having high coercive force and high maximum energy product with high productivity by employing a permanent magnet alloy, having a specific composition of R, boron, gallium and the remainder principally comprising iron, as a starting material and then crushing, pressing under magnetic field, and sintering the alloy.

CONSTITUTION: A permanent magnet alloy composed of 10-40wt.% of R (R represents at least one element selected from Y and rare earth elements), 0.1-8wt.% of boron, 13wt.% or less of gallium, and the remainder mainly comprising iron is employed as a starting material. 30wt.% or less of Co is also added to the permanent magnet alloy. 90wt.% or less of Ga is substituted by Al. The magnet alloy thus obtained (oxygen concentration is 0.05-0.03wt.%) is crushed roughly in Ar atmosphere and then crushed finely by a jet mill. The fine powder is filled in a predetermined die and

compression molded while applying magnetic field and then it is sintered in Ar atmosphere before it is subjected to aging in vacuum at 550-750° C.

LEGAL STATUS

[Date of request for examination] 08.11.1993

[Date of sending the examiner's decision 21.11.1997

of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number] 2868062

[Date of registration] 25.12.1998

[Number of appeal against examiner's 09-21321

decision of rejection]

[Date of requesting appeal against 18.12.1997

examiner's decision of rejection]

[Date of extinction of right]

Copyright (C); 1998,2003 Japan Patent Office